



KÖSTER Restoration Plaster Grey

Technical Data Sheet M 661 025

Issued: 2019-09-06

Off. Test Certificate, AMPA for stone and earth, Clausthal-Zellerfeld

Salt- and moisture resistant restoration plaster for inside and outside use

CE	KÖSTER BAUCHEMIE AG Dieselstraße 1-10, 26607 Aurich 13 M 661 EN 998-1:2010 Restoration Plaster (R) EN 998-1:2010 ZA.1
Compressive strength 28 d	CS II
Capillary water uptake	> 0.3 kg/m ² after 24 h
Tensile strength	0.08 N/mm ² failure type A
Dry density	category 2: water tight
Depth of water penetration	1.27 kg/dm ³
Coefficient of water vapor	μ 10
permeability	
Reaction to fire	A1

Features

KÖSTER Restoration Plaster Grey is a salt and pressure resistant restoration plaster for the restoration of heavily moisture and salt burdened substrates. Due to its high porosity and hydrophobicity, KÖSTER Restoration Plaster Grey allows for the damage free drying and de-salting of masonry even in the case of high salt contents. It improves the insulative properties of the wall and therefore helps prevent the formation of condensate. KÖSTER Restoration Plaster Grey is free of light fillers and therefore requires no further surface treatment prior to the application of breathable paints or wallpaper which is open to vapor diffusion.

Technical Data

Density of fresh mortar	1.3 kg / l
Porosity of fresh mortar	> 30 Vol%
Compressive strength (7 days)	>5.5 N / mm²
Flexural tensile strength (28 d)	> 2.5 N / mm ²
Porosity of cured plaster	> 40 Vol%
Setting time	approx. 3 hours
Modulus of elasticity	> 6500 N / mm ²
Water requirement per 25 kg bag	2.8 - 3.3 kg

Fields of Application

KÖSTER Restoration Plaster Grey is suitable for the repair of moisture and salt damaged masonry, also after the post installation of a horizontal barrier with KÖSTER Crisin 76, KÖSTER Mautrol, KÖSTER Mautrol 2C, or KÖSTER Mautrol Flex 2C. It can be applied to reduce the formation of condensate after waterproofing rooms with high humidity using mineral sealing slurries such as the KÖSTER KD-System or KÖSTER NB 1 Grey.

KÖSTER Restoration Plaster Grey can also be used as a water repellent exterior plaster. In the case of exterior application we recommend the application of KÖSTER Repair Mortar on the base area up to 30 cm above ground level.

Substrate

Suitable substrates include concrete, masonry consisting of brick, natural stone, porous concrete block, perforated brick, mixed masonry, etc., sealing slurries such as KÖSTER NB 1 Grey, KÖSTER NB 2 White, or the KÖSTER KD-System. Prior to the application of KÖSTER Restoration Plaster Grey, the substrate is primed with KÖSTER Polysil TG 500 with a minimum consumption of 120 g / m². Apply the KÖSTER Polysil TG 500 until the surface is saturated. In the case of strongly absorbent substrates the consumption can be up to 250 g / m². Loose particles and salt efflorescence should be removed mechanically prior to the beginning of the restoration. Substrates containing gypsum are not suitable substrates and the gypsum must be removed.

Application

KÖSTER Restoration Plaster Key Coarse

A plaster key is a thin slurry which is used as a bonding bridge between the substrate and the Restoration Plaster. The KÖSTER Restoration Plaster Key Coarse is cast onto the substrate with a brush or a trowel (Consumption approx. 4-6 kg / m^2) so that the plaster key is no thicker than 5 mm and covers approximately 50% of the area. After hardening (approx. after 30 to 60 minutes) the Restoration Plaster can be applied. The key coarse is made also of KÖSTER Restoration Plaster Grey with the addition of max. 10% KÖSTER SB bonding emulsion added to the mixing water (Consumption approx. 3 kg / m^2).

The waterproofing against pressurized and actively flowing water is carried out using the KÖSTER KD System. Approx. 24 hours after finishing the waterproofing, the Restoration Plaster Key is applied. After another 24 hours, KÖSTER Restoration Plaster Grey can be applied on top of the Restoration Plaster Key. After smoothing and curing, the surface of the restoration plaster can be covered with paints and wallpapers which are open to vapor diffusion without further pretreatment. When waterproofing against non-pressurized water and pressurized water without active leakages using KÖSTER NB 1 Grey and KÖSTER Polysil TG 500, the restoration plaster is thrown directly onto the last not yet cured layer of slurry without prior application of a plaster key.

Aftertreatment

If aftertreatment is required or desired, for example due to very dry conditions, the plaster can be treated according to the general practice for mortars, such as covering with a thin PE sheet.

Consumption

Approx. 12 kg/m² per cm layer thickness

On uneven surfaces additional consumption may have to be considered for levelling the surface.

Cleaning

Clean tools immediately after use with water.

The information contained in this technical data sheet is based on the results of our research and on our practical experience in the field. All given test data are average values which have been obtained under defined conditions. The proper and thereby effective and successful application of our products is not subject to our control. The installer is responsible for the correct application under consideration of the specific conditions of the construction site and for the final results of the construction process. This may require adjustments to the recommendations given here for standard cases. Specifications made by our employees representatives which exceed the specifications contained in this technical guideline require written confirmation. The valid standards for testing and installation, technical guidelines, and acknowledged rules of technology have to be adhered to at all times. The warranty can and is therefore only applied to the quality of our products within the scope of our terms and conditions, not however, for their effective and successful application. This guideline has been technically revised; all previous versions are invalid.

KÖSTER BAUCHEMIE AG • Dieselstraße 1-10 • D-26607 Aurich • Tel. 04941/9709-0 • Fax -40 • info@koester.eu • www.koester.eu



Packaging

M 661 025 25 kg bag

Store the material in a dry environment. In originally sealed packages, the material can be stored for a minimum of 12 months.

Wear protective gloves and goggles when processing the material. Observe all governmental, state, and local safety regulations when processing the material.

Related products

KÖSTER KB-FIX 5 Prod. code C 515 015 KÖSTER Polysil TG 500 Prod. code M 111 KÖSTER Restoration Plaster Key Coarse Prod. code M 154 025 KÖSTER Mautrol Liquid Sealant Prod. code M 241 KÖSTER Mautrol 2C Prod. code M 261 KÖSTER Mautrol Flex 2C Prod. code M 262 020 KÖSTER Crisin Cream Prod. code M 278 KÖSTER Crisin 76 Concentrate Prod. code M 279 KÖSTER Fine Plaster Prod. code M 655 025 KÖSTER Façade Cream Prod. code P 200 KÖSTER Silicone Paint White Prod. code P 260 010 KÖSTER KD System Prod. code W 219 KÖSTER NB 1 Grey Prod. code W 221 025 KÖSTER NB 2 White Prod. code W 222 025 KÖSTER Repair Mortar Prod. code W 530 025 KÖSTER Waterstop Prod. code W 540 015 KÖSTER SB Bonding Emulsion Prod. code W 710

The information contained in this technical data sheet is based on the results of our research and on our practical experience in the field. All given test data are average values which have been obtained under defined conditions. The proper and thereby effective and successful application of our products is not subject to our control. The installer is responsible for the correct application under consideration of the specific conditions of the construction site and for the final results of the construction process. This may require adjustments to the recommendations given here for standard cases. Specifications made by our employees or representatives which exceed the specifications contained in this technical guideline require written confirmation. The valid standards for testing and installation, technical guidelines, and acknowledged rules of technology have to be adhered to at all times. The warranty can and is therefore only applied to the quality of our products within the scope of our terms and conditions, not however, for their effective and successful application. This guideline has been technically revised; all previous versions are invalid.

KÖSTER BAUCHEMIE AG • Dieselstraße 1-10 • D-26607 Aurich • Tel. 04941/9709-0 • Fax -40 • info@koester.eu • www.koester.eu